

AMC Approved



STEEL-REINFORCED EPOXY PUTTY STICK

**Rebuild . . .**

- small engine parts
- seal leaks
- fill cracks and voids in metal
- fashion handles

**Form . . .**


- nuts and bolts
- repair stripped threads
- anchor machines

**Repair . . .**

- metal tools
- equipment ducts
- housing and appliances
- sink traps



- **The Ultimate for Small or Emergency Repairs**
- **Easy-To-Use and Mistake-Proof**
- **Bonds Instantly with Superior Strength**
- **Saves Hundreds of Dollars in Repairs**
- **Belongs in Every Toolbox**



Made in U.S.A.



**AMC**  
Marketing the Potential

## Product Description

FastSteel® Epoxy Putty Stick is a fast-setting, industrial-strength polymer compound that enables permanent repairs to anything made of steel or other metals. It also bonds to wood, glass, masonry, and many plastics. Each handy stick contains pre-measured portions of activator and base throughout – no measuring or mixing tools are necessary. As the epoxy is mixed, the two contrasting colors blend into one color to indicate complete mixing. The consistency (like modeling clay) eliminates drips and runs, facilitates adhesion to the substrate, and allows the material to be shaped and formed as needed before curing begins. FastSteel® epoxy cures to a dark gray metallic color. Once cured, it can be tapped, drilled, screwed, sawed, machined, ground, filed, or painted. It is non-rusting. Suitable for interior or exterior use, it is resistant to water, chemicals, and temperature extremes. FastSteel® epoxy contains no solvents or VOC's. It's non-flammable and releases no noxious fumes. It won't shrink or pull away. The unused portion stays fresh for future use when saved in its original package.

## Performance Data\*

SHELF LIFE (months @ 75°F, min)	24
HARDNESS, SHORE D (full cure, 1 hr.)	80
LAP SHEAR TENSILE STRENGTH (p.s.i.)	
On Steel	900
COMPRESSIVE STRENGTH (p.s.i.)	12,000
DENSITY (gm/cm³, lb/gal)	2.2, 18.5
SHRINKAGE (%)	<1
NON-VOLATILE CONTENT (%)	100
ELECTRICAL RESISTANCE (megohms)	30,000
DIELECTRIC STRENGTH (volts/mil)	300
UPPER TEMPERATURE LIMIT	
Continuous (°F)	250
Intermittent (°F)	300

### CHEMICAL RESISTANCE

Resistant to hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions and dilute acids and bases.

\*Typical properties: for information only; not for specification purposes.

## Packaging Options

FastSteel® epoxy is available in 3 1/2"(2 oz.) and 7" (4 oz.) lengths. Individually packaged in reusable clear plastic tube with tri-lingual (English, Spanish, French) instructions and plastic friction top. Packed 12 sticks in display carton – 2 display cartons per master carton, or 24 sticks per shipper carton. 3 1/2" sticks are also available in blister packs (12 per carton).



Pop-Up  
Cardboard  
Display Carton



Blister  
Packs



Acrylic Display  
Racks

[www.amc-products.com](http://www.amc-products.com)  
[info@amc-products.com](mailto:info@amc-products.com)

## How To Use

Before applying, roughen and clean the area to be repaired. Then follow these easy steps.



1. **Cut** or twist off required amount.
2. **Mix** by kneading with fingers to a uniform color. If mixing is difficult, warm FastSteel® epoxy to room temperature or slightly above.
3. **Apply** to surface to be repaired (within two minutes of mixing). Force into any cracks or holes and strike off excess material, preferable with a tool wet with clean water.

*When applying to a damp, wet or slowly leaking area, work the material forcefully into the surface and apply pressure until adhesion begins to take effect.*

**For Best Results:** Use damp fingers for easier mixing and application. Remove excess material before hardening begins.

**Curing:** FastSteel® epoxy has a work life of approximately 3 minutes. After 5–10 minutes it will harden and form a tenacious bond. After 60 minutes, the system can be put back into service.

**WARNING**

- May cause irritation to sensitive skin. Wash hands with soap and water after use.
- May be harmful if swallowed.
- Eye irritant. In case of eye contact, flush with water. Contact physician.
- Keep out of reach of children.
- Not intended for use in structural applications.
- When sanding cured putty and substrate, use protective eye wear and dust mask.

**USDA** Acceptable for use in federally inspected meat and poultry plants



Certified by The National Sanitation Foundation for use in contact with drinking water.



Certified by The American Bureau of Shipping for use on marine vessels.

## Applicable Standards

**AMC**  
Marketing the Potential

For More Info, Contact Us:

Unit 230, 12417 No. 2 Road  
Richmond BC, Canada V7E 2G3  
Toll Free: 1-888-680-2886  
Fax: 1-877-241-9890